

AS/NZS 3678 - 350

XLERPLATE® steel

DATE: AUGUST 2009

PRODUCT DESCRIPTION

- A high strength structural steel product with nominal yield strength of 350 MPa

SUPPLY CONDITIONS

- Thickness Range: 5mm – 100mm (thicknesses greater than 80mm are available by enquiry)
- Availability: Plate is available in standard sizes. For sizes outside the standard plate offer refer to XLERPLATE® steel Size Schedule 2.
- Edge Condition: Untrimmed (Mill Edge) / Trimmed
- Tolerances: AS/NZS 1365
- Ultrasonic Inspection: AS1710 available
- Surface Inspection: BlueScope Steel (third party available)
- Certification: BlueScope Steel (third party endorsed available)

(1) Optional supply condition. May be subject to size range restrictions.

TYPICAL USES

- General fabrication
- Structural members
- High-rise buildings
- Bridges
- Storage tanks

FEATURES & BENEFITS

- Guaranteed minimum strength levels
- Excellent weldability
- Good formability

WARNINGS

- This material should be used in conjunction with the appropriate structural design and welding standards.
- Maximum recommended temperature for hot forming 620°C. If heated above 620°C, mechanical properties may deteriorate.
- An untrimmed (Mill) edge may contain minor surface discontinuities as a result of the rolling process (refer Clause 7 AS/NZS 3678). It is recommended that a minimum of 50mm be removed from each untrimmed edge.
- Where impact testing is required refer to AS/NZS 3678 - 350L15.

NEAREST OVERSEAS SPECIFICATIONS

ASTM A572-50 ISO 630-E355B JISG 3106-SM490A EN 10025-2-S355JR

For more information contact:

BlueScope Steel Direct

Phone: 1800 800 789

Email: steeldirect@bluescopesteel.com

Website: www.xlerplate.com.au

Date Published: August 2009. The information contained in this datasheet is provided by way of general information only, and should not be relied upon by any person. You must seek specific advice as to the suitability of this product for the purpose for which, and the manner in which, you propose to use it. This may involve further independent analysis and testing. BlueScope Steel Limited and its related bodies corporate take no responsibility for any adverse consequences of any nature which arise as a result of reliance on this datasheet. These datasheets will be updated from time to time and the most up-to-date versions are available from www.xlerplate.com.au

XLERPLATE® is a registered trade mark of BlueScope Steel. BlueScope is a trade mark of BlueScope Steel Limited ABN 16 000 011 058.



AS/NZS 3678 - 350

XLERPLATE® steel

CHEMICAL COMPOSITION						
Element	Guaranteed Maximum % ⁽²⁾	Typical % Thickness (mm)				
		5 ≤ t	5 < t < 8	8 ≤ t ≤ 25	25 < t ≤ 80	80 < t ≤ 100 ⁽³⁾
Carbon	0.22	0.155	0.14	0.15	0.09	0.13
Silicon	0.55	0.15	0.20	0.30	0.35	0.45
Manganese	1.70	0.65	1.10	1.20	1.50	1.50
Phosphorus	0.040	0.020	0.020	0.020	0.020	0.020
Sulfur	0.030	0.010	0.010	0.010	0.010	0.003
Aluminium	0.100	0.030	0.035	0.025	0.035	0.035
Micro alloys - Nb ⁽⁴⁾	0.150	-	-	-	0.025	0.015
(when added) - Ti	0.040	-	0.018	0.018	0.018	0.018
CEQ (IIW) ⁽¹⁾	0.48	0.27	0.33	0.36	0.35	0.41

$$(1) \text{ CEQ (IIW)} = C + \frac{\text{Mn}}{6} + \frac{(\text{Cr} + \text{Mo} + \text{V})}{5} + \frac{(\text{Cu} + \text{Ni})}{15}$$

(2) All values shown refer to the relevant Australian Standard unless stated otherwise

(3) Additional Alloys 0.2 Ni, 0.3 Cu

(4) Niobium + Vanadium + Titanium ≤ 0.15%

MECHANICAL PROPERTIES							
Tensile Properties (Transverse)		Thickness Range (mm)					
		8 ≤ t	8 < t ≤ 12	12 < t ≤ 20	20 < t ≤ 25	25 < t ≤ 80	80 < t ≤ 100
Guaranteed Min.	Yield Strength (MPa)	360	360	350	340	340	330
	Tensile Strength (MPa)	450	450	450	450	450	450
	Elong. on 5.65 √ So (%)	20	20	20	20	20	20
Typical	Yield Strength (MPa)	410 - 540	380 - 440	360 - 420	350 - 440	350 - 420	350 - 410
	Tensile Strength (MPa)	480 - 590	470 - 550	470 - 550	470 - 550	460 - 530	500 - 550
	Elong. on 5.65 √ So (%)	20 - 33	22 - 35	23 - 33	23 - 33	25 - 35	25 - 35
Charpy Impact Properties - Longitudinal at -15°C on 10 x 10mm specimen		Absorbed Energy (joules)					
		Avg. of 3			Ind.		
Typical as rolled		50 - 200			30 - 250		

AS/NZS 3678 - 350

XLERPLATE® steel

WELDABILITY						
	Guaranteed Maximum	Typical Group / Thickness (mm)				
		$5 \leq t$	$5 < t < 8$	$8 \leq t \leq 25$	$25 < t \leq 80$	$80 < t \leq 100$
Group 5 ⁽⁵⁾	5	1	2	3	3	4

(5) Refer to WTIA Technical Note 1 or AS/NZS 1554.1

FORMABILITY (recommended min. inside radii)			HARDNESS
$t \leq 20\text{mm}$	Long 3.0T	Trans 2.0T	Typical
$20 < t \leq 25\text{mm}$	Long 3.75T	Trans 2.5T	140 - 180 BHN
$t \leq 25\text{mm}$	Hot form (max 620°C)		